

Tabla comparativa de durezas

Dureza Brinell HB	Dureza Rockwell		Dureza Vickers
	HRB	HRC	
80	36.4		80
85	42.4		85
90	47.4		90
95	52.0		95
100	56.4		100
105	60.0		105
110	63.4		110
115	66.4		115
120	69.4		120
125	72.0		125
130	74.4		130
135	76.4		135
140	78.4		140
145	80.4		145
150	82.2		150
155	83.8		155
160	85.4		160
165	86.8		165
170	88.2		170
175	89.6		175
180	90.8		180
185	91.8		185
190	93.0		190
195	94.0		195
200	95.0		200
205	95.8		205
210	96.6		210
215	97.6		215
220	98.2		220
225	99.0		225
230		19.2	230
235		20.2	235
240		21.2	240
245		22.1	245
250		23.0	250
255		23.8	255
260		24.6	260
265		25.4	265
270		26.2	270
275		26.9	275
280		27.6	280
285		28.3	285
290		29.0	290
295		29.6	295
300		30.0	300
310		31.5	310
320		32.7	320
330		33.9	330
340		34.9	340
350		36.0	350

Dureza Brinell HB	Dureza Rockwell		Dureza Vickers
	HRB	HRC	
359		37.0	360
368		38.30	370
376		38.9	380
385		39.8	390
392		40.7	392
400		41.5	410
408		42.4	420
415		43.2	430
423		44.0	440
430		44.8	450
		45.5	460
		46.3	470
		47.0	480
		47.7	490
		48.8	500
		49.0	510
		49.8	520
		50.3	530
		50.9	540
		51.5	550
		52.1	560
		52.7	570
		53.3	580
		53.8	590
		54.4	600
		54.9	610
		55.4	620
		55.9	630
		56.4	640
		56.9	650
		57.4	660
		57.9	670
		58.4	680
		58.9	690
		59.3	700
		60.2	720
		61.1	740
		61.9	760
		62.7	780
		63.5	800
		64.3	820
		65.0	840
		65.7	860
		66.3	880
		66.9	900
		67.5	920
		68.0	940